

## Technical Information

## ACCUREL® XP100-84

## Product Composition

Porous carrier resin completely made from polypropylene.

## Physical Properties

|                |                            |
|----------------|----------------------------|
| Melt flow rate | 2.1 (230 °C, 2.16 kg)      |
| Bulk density   | 75 – 115 kg/m <sup>3</sup> |
| Void content   | 79 – 89 %                  |
| Colour         | white/offwhite             |
| Delivery form  | pellets                    |
| Pellet size    | 2 – 4 mm                   |

## Application

ACCUREL® XP100-84 is a porous carrier for the production of additive masterbatches via absorption of liquid additives at processing temperatures up to 100 °C.

ACCUREL® XP100-84 is most effective for the incorporation of thermally sensitive additives, reactive agents, fragrances and for those which cannot be processed by conventional extrusion compounding techniques.

In general, additive viscosity should not exceed 30,000 cSt at absorption processing temperature.

## Benefits

- up to 65% additive content
- no additional heat history for the additive
- pre-dispersed additive in the porous structure of the carrier resin
- dosage like conventional masterbatches

## Additive Absorption Process

For details concerning the loading of ACCUREL® XP100-84 pellets we refer to the technical information 'Additive Loading in ACCUREL® MP/XP Carriers'.

## Food Contact Status

ACCUREL® XP100-84 complies with the EU and FDA food contact regulations.

## Registration Status

ACCUREL® XP100-84 complies with REACH Regulation (EC) No 1907/2006 and the HDPE grade used for Accurel XP100-84 is listed / complies with the following chemical inventories:

EINECS (exempt), TSCA, DSL, ENCS, IECSC, KECL

## Storage Stability

60 months after date of production under normal good storing conditions.

## Packaging

25 kg net in a cardboard box with PE inliner  
200 kg net (8 x 25 kg)

## Product Safety

For transport, handling and first aid instructions we refer to the material safety data sheet for ACCUREL® XP100.

05/2018

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Evonik Nutrition & Care GmbH**  
Goldschmidtstraße 100  
45127 Essen, Germany  
Phone Europe +49 201 173 2665  
Phone Asia +86 21 61191 125  
Phone Americas +1 804 727 0700  
[interface-performance@evonik.com](mailto:interface-performance@evonik.com)  
[www.evonik.com/interface-performance](http://www.evonik.com/interface-performance)